

graboSport PRIMA			
<i>Property</i>	<i>Standard</i>	<i>Unit</i>	<i>Result</i>
DESCRIPTION			
Surface	-	-	TECH Surface
Backing	-	-	Closed cell double foam
Thickness	EN 428	mm	4,5
Weight	EN 430	kg/m ²	2,8
Width	EN 426	m	2
Standard roll length	EN 426	m	20 ± 10%
Maximal roll length	EN 426	m	25
CLASSIFICATION			
Product specification	Vinyl indoor sport floor		
Thermal resistance	-	m ² k/W	0,04
Reaction to fire	EN 13501	-	C _{fl} -s1
Formaldehyde emission	-	-	No formaldehyde
Pentachlorophenol	-	-	No pentachlorophenol
SPORT PROPERTIES			
Friction	EN 13036-4	-	80-110
Shock absorption	EN 14808	%	19
Vertical deformation	EN 14809	mm	0,7
Ball rebound	EN 12235	%	98
Specular gloss	EN 2813	%	< 30
TECHNICAL CHARACTERISTICS			
Dimensional stability	EN 434	%	± 0,2
Resistance to rolling load	EN 1569	N	1500
Colour fastness	ISO 105 B02	-	6
Chemical resistance	EN 423	-	no change
Abrasion resistance	EN ISO 5470-1	mg/1000cycles	< 250
OTHERS			
Limited warranty		10 years	
Cleanability		TECH Surface - Easy to clean	
Antimicrobial treatment		graboSAN	
Enviromental attributes	 	No periodic renewal needed; Solvent and heavy metal free	

GRABOPLAST Floor Covering Manufacturers Ltd.
H-9023 Győr, Fehérvári út 16/b tel.: (36) 96 506 100
mail@graboplast.hu www.graboplast.hu